

CLAY GC-5

L.O.I.	%	7,50
SiO ₂	%	56,98
Al ₂ O ₃	%	26,19
TiO ₂	%	0,86
Fe ₂ O ₃	%	3,19
CaO	%	0,21
MgO	%	0,94
Na ₂ O	%	0,29
K ₂ O	%	3,72

Temperature (C)	(°C)	1185
Fired Color L		73,1
Fired Color +a		5,8
Fired Color +b		23,33
Water Abs.	(%)	1,42
Fired Shrinkage	(%)	9,89

+ 63 Micron	(%)	1,45
+ 150 Micron	(%)	1,23

Density (g/l)	(g/l)	1654
Na ₂ SiO ₃ (Sodium Silicate)	(%)	1